

BISALLOY® ARMOUR HHA 500 STEEL

Introduction

BISALLOY® ARMOUR HHA500 steel (High Hardness Armour) - a quenched and tempered steel armour plate suitable for use in both military and civil applications where light weight and resistance to ballistic projectiles is required.

Brinell hardness

Thickness (mm)	Specification	Typical
5 - 50 ¹	477 - 534 HB	500 HB

Tensile properties

Property	Typical
0.2% Proof Stress	1300 MPa
Tensile Strength	1640 MPa
Elongation in 50 mm G.L.	10%

Charpy impact values

Thickness (mm)	Test Piece	Test Temp	Min. Energy (Transverse)	Min. Energy (Longitudinal)
5	10 x Thk	-40°C	By Agreement	By Agreement
6 - <8	10 x 5	-40°C	8 J	10 J
8 - <12	10 x 7.5	-40°C	12 J	15 J
≥12	10 x 10	-40°C	16 J	20 J

Chemistry

The chemical specification conforms to the requirements of MIL-DTL-46100, although it is tighter than the requirements of that specification so as to optimise the material's performance. Product chemical analyses are taken on a per-heat basis. Chemical analysis is as follows:

Chemical composition

Thickness (mm)	Weight %	C	P	Mn	Si	S	Ni	Cr	Mo	B	CE(IIW)	CET
5 - 50 ¹	Maximum	0.32	0.025	0.80	0.50	0.005	0.50	1.20	0.30	0.002	0.61*	0.40*

Thickness tolerance

Thickness (mm)	Special Tolerance
5 - 25	-0.0 + 1.0
>25 - 50	-0.0 + 1.2

Test frequency

Per Plate	Per Batch	By Agreement
Hardness	Charpy (L), Charpy (T)	Thickness, Tensile, Ballistic Properties, Product Analysis

PRODUCT DATA SHEET



BISALLOY® ARMOUR HHA 500 STEEL

Other

Equivalent Specification	Surface Finish
MIL - DTL - 46100	Shotblasted

Fabrication

For advice on fabrication refer to relevant Bisalloy technical brochures.
Contact Bisalloy direct or visit www.bisalloy.com.au

* Typical for 12mm plate

† Other thicknesses may be available on application

PLEASE NOTE: Every care has been taken to ensure the accuracy of information contained in this manual which supersedes earlier publications, however Bisalloy Steels shall not be liable for any loss or damage whatsoever caused from the application of such information. Typical values are provided for reference information only and no guarantee is given that a specific plate will provide these properties. Information is subject to change without notice. **Published November 2019**



02 4272 0444 | www.bisalloy.com.au

BIS0421 - BISALLOY® ARMOUR HHA 500 STEEL - NOVEMBER 2019

BISALLOY is a registered trade mark of Bisalloy Steels Group Limited, ABN 22 098 674 545